

# LAMINATED WALL INSULATION

## CONTINUOUS EXTERIOR INSULATION

Insulation is a vital component of a building's envelope. For building designers requiring the highest quality rigid insulation for wall applications, ThermalStar® Laminated Wall Insulation (LWI) provides unmatched quality, with a stable long term R-value that will last the lifetime of your structure.

Manufactured under an industry leading quality control program monitored by UL and ICC-ES, ThermalStar LWI meets or exceeds ASTM C578 standards, providing an HFC free, recyclable rigid insulation with a low Global Warming Potential (GWP).

### PHYSICAL PROPERTIES

PROPERTY	ASTM TEST METHOD	LWI SHEETS		LWI FANFOLD	
		10	15	10	15
Compressive Strength (psi) at 10% Deformation <sup>1</sup>	D1621	10	15	10	15
ASTM Classification	C578	Type I	Type II	Type XI	Type II
R-value per inch at 75°F Mean Temperature	C518	3.9	4.2	3.6	4.2
R-value per inch at 40°F Mean Temperature	C518	4.2	4.6	3.9	4.6
R-value per inch at 25°F Mean Temperature	C518	4.4	4.8	4.1	4.8
Flexural Strength (psi)	C203	25	35	25	35
Water Absorption (% by volume) 24 Hour Immersion	C272	1.0	1.0	1.0	1.0
Water Vapor Permeance (perms)	E96	0.3	0.3	0.3	0.3
Surface Burning - Flame Spread	E84	<25	<25	<25	<25
Surface Burning - Smoke Developed	E84	<450	<450	<450	<450
Maximum Use Temperature	-	Short Term (10-15 minutes) 180°F, Long Term 165°F			

<sup>1</sup> ThermalStar LWI is elastic up to 1% deformation. A safety factor of 3 is recommended for long term loads to minimize long term deflection.

## CODE COMPLIANCE

ThermalStar LWI complies with the model building codes when properly installed, as found in the following code reports and classification listings:

- ASTM C578 – (See product marking for type)
- Physical Properties – UL QORW.R16529
- Surface Burning – UL BRYX.R16529
- CAN/ULC-S102.2, S701 – ULC BOZCC.R16529
- International Energy Conservation Code (IECC) – ICC-ES ESR-1962, UL ER16529-01
- International Residential Code (IRC) – ICC-ES ESR-1962, UL ER16529-01
- International Building Code (IBC) – ICC-ES ESR-1962, UL ER16529-01
- California Certified Insulation Material - License T 1472

## WARRANTY

ThermalStar LWI is backed by a limited lifetime warranty for physical and thermal performance. See separate ThermalStar warranty for terms and conditions.

## STANDARD PRODUCT OFFERINGS

COMPRESSIVE STRENGTH	10 psi, 15 psi
SIZE	4'x8' sheets, 4'x50' fanfold
SHEET THICKNESS	3/4", 1", 1-3/16", 1-1/2", 2", 2-3/8", 3"
FANFOLD THICKNESS	3/8", 1/2"

FOR ADDITIONAL RESOURCES, VISIT THE WALL INSULATION SECTION OF OUR WEBSITE [ATLASMOLDEDPRODUCTS.COM](https://www.atlasmoldedproducts.com)

GREATER COVERAGE  
GREATER AVAILABILITY



Atlas Molded Products, a Division of Atlas Roofing Corporation  
8700 Turnpike Drive, Suite 400, Westminster, CO 80031  
Phone: 855.597.4427 | Fax: 303.428.2595 | [AMPinfo@AtlasRoofing.com](mailto:AMPinfo@AtlasRoofing.com)

